

Alcord Al has a special coating for welding aluminium. When welding, hold the electrode at a right angle to the workpiece, with a short arc. Wall thicknesses greater than 10 mm and larger workpieces will require preheating from 150°C to 250 °C. Since slag residues are corrosive, they must be completely removed from the weld bead. Alcord AL may be used for oxy flame welding. The covering being hygroscopic, electrodes must be stored in an absolutely dry location, or redried if required.

Classification	
AWS	A5.3: E1100
DIN	1732: EL-Al 99,5

Approvals	Grades

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Zn	Ti	Mg	Fe	Cu	Al
-	-	-	-	-	-	-	-	-	-	-	99.80

All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation A5 (%)	Impact Energy ISO - V (J)	Hardness
As Welded	≥ 30	≥ 80	≥ 30	-	-

Materials

Al 99,5 ;Al 99, Al 99,9 Mg 0,5, AlMg 0,5

Storage and redrying

Keep dry and avoid condensation.
Once opened, store at 90-120 °C until used.
If necessary, Re-dry at 110-120 °C for 2 hours, 5 times max.

Current condition and welding position

DC+



Packaging data

Diameter (mm)	Length (mm)	Current (A)	Electrode average weight (g)	Weld metal weight per electrode (g)
2,5	350	60-90	9,2	5,0
3,2	350	80-110	14,0	8,4