

MIG-MAG Wires C-Mn and low-alloy steels

Carbofil is a copper coated solid wire suitable for welding with CO₂ or mixed shielding gases. Excellent mechanical properties. Carbofil is used for a very wide range of structural steel applications. Good x-ray quality.

Classification	
AWS	A5.18: ER 70S-3
EN	440: G 42 A M G2Si1
EN	440: G 42 A C G2Si1

Approvals	Grades

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V	N	Cu
0.07	1	0.65	≤ 0.025	≤ 0.025	-	-	-	-	-	-	-

All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation A5 (%)	Impact Energy ISO - V (J) 0°C	Hardness
As Welded	≥ 420	480-550	≥ 22	≥ 90	-

Gas test: Acc. To EN 439: M21(Arcal 21-Atal 6)

Shielding Gas: Acc. To EN 439: M21(Arcal21-Atal6) or C1(Arcal 2)






Materials

S(P)235 to S(P)355; GP240; GP280

Storage

Keep dry and avoid condensation

Current condition and welding position

DC+					
					
PA	PB	PC	PG	PF	PF2

Packaging data: K300 Kg, 16

Diameters	0,6	0,8	1,0	1,2	1,6	
-----------	-----	-----	-----	-----	-----	--