

MIG-MAG Wires C-Mn and low-alloy steels

Carbofil Ni2 is a copper coated solid wire suitable for the welding of alloyed steels, and 2%Ni steels for low temperature applications. Excellent mechanical properties.

Classification	
AWS	A5.28: ER 80S-Ni2
EN	440: G 46 6 M G2Ni2

Approvals	Grades

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V	N	Cu
0.08	1.10	0.50	≤ 0.020	≤ 0.020	-	2.50	-	-	-	-	-

All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation A5 (%)	Impact Energy ISO - V (J) -60°C	Hardness
As Welded	≥ 470	550-680	≥ 20	≥ 47	-

Gas test: Acc. To EN 439: M21(Arcal 21-Atal 6)

Shielding Gas: Acc. To EN 439: M21(Arcal 21-Atal 6)

Materials

S(P)275-S(P)420

Storage

Keep dry and avoid condensation.

Current condition and welding position

DC +



Packaging data: K300 Kg. 16

Diameters	0,8	1,0	1,2			
-----------	-----	-----	-----	--	--	--