

CARBOFIL CrMo 5

MIG-MAG Wires C-Mn and low-alloy steels

Carbofil CrMo5 is a copper coated solid wire suitable for welding creep resistant 5,5% Cr 0,5% Mo steels, including chemical and ammonia synthesis applications. Pre-heating and interpass temperatures in the range 250-300°C are recommended.

Classification	
AWS	A5.28: ER 80S-B6
EN	12070: G CrMo5

Approvals	Grades
-----------	--------

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V	N	Cu
0.07	0.50	0.50	≤ 0.020	≤ 0.020	5.70	-	0.60	-	-	-	-

All-weld metal Mechanical Properties

Heat Treatment	Yield Strength N/mm ²	Tensile Strength N/mm ²	Elongation A5 (%)	Impact Energy ISO - V (J) 20°C	Hardness
PWHT 760°C x 1h	≥ 470	≥ 590	≥ 17	≥ 47	-

Gas test: Acc. To EN 439: M21(Arcal 21-Atal 6)

Shielding Gas: Acc. To EN 439: M21(Arcal 21-Atal 6)

Materials


12CrMo19-5, X12CrMo5; A182 Gr. F5, A199 Gr. T5, A213 Gr.T5, A335 Gr.P5
A 336 Cl. F5, A 369 Gr. FP5, A 387 Gr.5, Cl 1 and 2

Storage

Keep dry and avoid condensation.

Current condition and welding position

DC+



Packaging data: K300 Kg. 16

Diameters	1,0	1,2	1,6			
-----------	-----	-----	-----	--	--	--