

SUPRASTRIP 309L

Classification

AWS A5.9: EQ309L

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite
0.015	1.60	0.40	-	-	23.60	13.30	-	-	-	-	-

SUPRASTRIP 430

Classification

AWS A5.9: EQ430

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite

SUPRASTRIP 308L

Classification

AWS A5.9: EQ308L

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite
0.012	1.90	0.30	-	-	20	10.50	-	-	-	-	-

SUPRASTRIP 309LMo

Classification

AWS A5.9: EQ309LMo

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite
0.015	1.80	0.30	-	-	24	13	3	-	-	-	-

SUPRASTRIP 316L

Classification

AWS A5.9: EQ316L

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite
0.014	1.60	0.35	-	-	18.70	12.60	2.70	-	-	-	-

SUPRASTRIP 347

Classification

AWS A5.9: EQ347

Analysis of all-weld metal (Typical values in %)

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	Cu	N	Ferrite
0.053	1.40	0.30	-	-	19.50	10.10	-	0.57	-	-	-